

A tiny, shrunken version of the running bond seem in masonry is combined with sheen and texture to create a simple but contemporary version akin to a woven fabric.

	US UNITS	METRIC UNITS
Total Weight	20.0 oz PLY 13.3 oz PSY	618 g PLM 451 g PSM
Roll Width	52/54 in.	132/137 cm
Gauge (avg)	0.24 in.	0.61 mm
Fabric	Non-Woven	
Tensile (Minimum)	50 x 55 lb _f	222 x 245 N
Tear (Minimum)	25 x 25 lb _f	111 x 111 N
Federal Spec	CCC-W-408D, Type II	
WA Spec	WA-101, Type II	
ASTM F-793	Category V, Type II	
Fire Testing	NFPA 101® Life Safety Code® NFPA 255 (ASTM E-84, CAN S102M) Tunnel Test ¹ Class A Rating Flame Spread 10 Smoke Developed 5 NFPA 286 Corner Burn Test ² Meets requirements for Flame Spread, Smoke Developed and Flashover EU classification in accordance with EN 13501-1:2007 and EN-15102-2008	
Indoor Air Quality	California 01350 - Meets emission requirements for schools and offices	
Repeat	Vertical N/A Horizontal N/A Nominal Pattern Width 51 in. Match Information Random Match, Reverse Hang	130 cm
1 When applied to GRC Board with A-848-B adhesive	2 When applied to 5/8" Type-X gypsum board with A-848-B adhesive	

Available in 24 Colorways

8721-64 Alloy	8721-10 Bone	8721-91 Ebony Glaze*
8721-48 Amber	8721-38 Buff	8721-35 Ecru
8721-87 Antique Bronze*	8721-85 Café Noir	8721-41 Falcon
8721-26 Ash	8721-80 Celadon	8721-59 Khaki
8721-88 Asparagus	8721-50 Charcoal	8721-19 Linen
8721-79 Bazaar	8721-57 Coconut	8721-75 Midnight
8721-22 Beige	8721-72 Cornflower	8721-89 Moss
8721-34 Bisque	8721-16 Cornsilk	8721-54 Quartz

*** These decorative metallic wallcoverings should only be cleaned with mild ingredients such as soap, detergent and water. Stronger, more alkaline household cleaners have the potential to damage the surface of the material along with excessive scrubbing.**

Vinyl wallcovering has a multitude of characteristics that allow it to provide an attractive and serviceable wall surface. One of the characteristics of vinyl wallcoverings is very low moisture permeability. Therefore, it is important to assure that there are no deficiencies in the design, construction and maintenance of a building that allows moisture to accumulate in a wall cavity. The use of a vinyl wallcovering in such a deficient circumstance would result in the vinyl wallcovering acting as a vapor barrier and restricting the passage of the moisture and increasing the chance of mold growth. It is recommended that walls be checked with a suitable moisture meter prior to installation and the moisture content should not exceed 4%. Wallcovering should not be installed on a wall until water/moisture incursion has been eliminated. On renovation projects, examine walls that are to receive wallcovering and assure they do not exhibit any mold/mildew. All mold and mildew must be removed and surfaces treated to inhibit future growth. In order to reduce the risk of mold/mildew, RJF International Corporation utilized an inhibitor in the wallcovering. The company can also provide a service of microventing the wallcovering whereby more than 25,000 micro-holes /ft² are fused through the vinyl thereby making it permeable.